



TTPVDF25

PVDF Extrusion & Injection Molding Resin

Description

TTPVDF25 is a low viscosity, melt processable, homopolymer of vinylidene fluoride. It has high mechanical strength, toughness and corrosion resistance. **TTPVDF25** exhibits good extrusion processing characteristics and can be readily injection molded. Conformable to Q/DYS 014-2015

TTPVDF25 is readily pigmented to a variety of colors using PVDF based wire and cable color concentrates.

Application

TTPVDF25 is intended for use as high temperature wire insulation and cable jacket. TTPVDF25 is also used in tubing, film, injection molding and transfer molding applications.

Safety Precautions

Adequate ventilation in properly maintained processing and handling areas will eliminate known hazards to personnel. Resin containers should be opened and used in well ventilated areas.

Equipment used to process at melt temperatures should be provided local exhaust ventilation to completely remove all fumes and vapors from the processing area. Additionally, care should be exercised to avoid the contamination of cigarettes and other forms of smoking tobacco when using fluoroplastic resins. Before processing any fluoroplastics, read the Safety Data Sheet available upon request. Also read the detailed information in the latest edition of the "Guide to the Safe Handling of Fluoropolymer Resins" published by the Fluoropolymers Division of the Plastics Industry Association (www.plasticsindustry.org/supply-chain/material-suppliers/fluoropolymers-division).

Product Packaging

- 20 kgs woven plastic bags with inner antistatic polyethylene liner.
- 40 kgs plastic circular drums
- 500 kgs Bulk Bag
- 1 MT Bulk Bag

Storage

The properties of **TTPVDF25** are not affected by storage time. Ambient storage conditions should be free of airborne contamination and water condensation when opening and emptying the package. Recommended storage temperature range 5 to 30°C.

Transportation

The product should be transported as a non-dangerous product, avoiding heat, moisture and strong shock.

Physical Properties	Typical Value ⁽²⁾	Unit	Test Method ⁽¹⁾
Specific Gravity	1.77 to 1.79		ASTM D 792
Melting Point	165 to 175	°C	ASTM D 3418
Melt Index (230°C, 5 kgs)	≥25.1	(g/10 min)	ASTM D 2116
Tensile Strength	5,075 (35)	psi (MPa)	ASTM D 638
Ultimate Elongation	25	%	ASTM D 638
Thermal Decomposition ≥	380	°C	TGA, 1% Wt. Loss N ₂
Hardness	70 to 80	Shore D	ASTM D 2240

(1) Tested in accordance with the latest issue of the designated Test Methods.

(2) Data represents typical values and should not be used for specification work.

General Processing Guidelines

The extrusion, tooling and molding machines used for **TTPVDF25** should be constructed of high nickel alloy corrosion-resistant materials and capable of operating at temperatures up to 300°C (572°F). TTPVDF25 is typically applied as a wire insulation and cable jacket using tubing techniques and Draw-Down Ratios (DDR) generally ranging from 30:1 to 80:1. Higher DDRs usually allow for greater line speed. A draw-ratio balance (DRB) ranging from 0.9 to 1.1 is recommended. A controlled vacuum is required at the rear of the crosshead to adjust the melt cone to the desired length. A melt cone that is too long results in excessive variations while a melt cone that is too short result in excessive spark failures and cone breaks. An electric wire preheater located as close to the crosshead as possible is recommended for preheating the wire. Although the amount of preheat will depend on the application. The coated wire should pass through an air gap followed by a warm-water quench at (110 °F to 150 °F) to allow uniform cooling and prevent the formation of shrinkage voids in the insulation. The cooling is highly dependent on the thickness of the insulation.

Color Concentrates: PVDF based on color concentrates are commercially available from several manufacturers. Your M. Holland representative can recommend color concentrates for your particular application

Typical Temperature Profile for Extruding TTPVDF25

	°C	°F
Zone 1	180 - 200	356 - 392
Zone 2	200 – 220	392 - 428
Zone 3	210 – 230	410 - 446
Zone 4	210 – 230	410 - 446
Breaker	220 – 240	428 - 464
Head	220 – 240	428 - 464
Die	220 – 240	428 - 464

1 Based on a 60 mm extruder with a 30:1 L/D; adjustments may be needed for other equipment.

2 For a smaller machine, it will be necessary to raise the temperature to ensure that the resin is completely melted before entry into the extruder's transition zone. A surging output at the idle could be caused by incomplete melting.

3 Process temperatures should be below 350°C to avoid any emission of toxic gas.

The process recommendations are general recommendations and modifications for individual machines and run conditions might be necessary.

Liability

Information contained in this publication is accurate to the reasonable knowledge of the publisher. M. Holland does not accept any liability whatsoever arising out of the use of the information in this document or the use, application, adaptation or processing of the products described herein.

All information is given in good faith, without warranty, representation, inducement or license of any kind. No guarantee is given that M. Holland products will be suitable in purchasers' constructions or processes for any particular end use. No one is authorized to make representations or give warranties or assume any other liabilities on behalf of M. Holland except if in writing and signed by a duly authorized M. Holland employee.

The purpose of the information contained herein is to assist our present and potential customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products and to consult the related Material Safety Data Sheet before use in order to satisfy itself as to the contents of the products and the suitability of the products for the customer's particular purpose. Although the information contained herein is to our knowledge accurate and reliable as of the date hereof, nothing herein shall constitute any warranty (express or implied, of merchantability, fitness or otherwise) and no statement herein shall be construed as an endorsement of any product or process. M. Holland shall not be liable for special, incidental, or consequential damages arising out of the use of the products based upon a breach of warranty, breach of contract, negligence, strict tort liability or any other legal theory.