



PR-2003 Black

Ultraviolet & Track Resistant Test Data

Description

PR-2003 BLACK is a linear low density polyolefin concentrate which when blended at 5% with HDPE base resin and various moisture cure resins, offers an excellent balance of ultraviolet protection and track resistance.

Applications and Uses

PR-2003 BLACK blended with HDPE base resin can be used as an insulating material for 5 to 15 kV Spacer Cable – Tree Wire. Used for primary and secondary wire insulation for overhead distribution. The blend of PR- 2003 and HDPE is effective in preventing direct shorts and flashovers should tree limbs or other objects come into contact with the conductor.

Tree wire & Spacer Cable.

Typical Test Data

PROPERTY	UNIT	SPECIFICATIONS	TEST METHOD	TEST RESULTS
ASH CONTENT	%	TEST & RECORD	ASTM D-1603	25.7
MELT FLOW INDEX	g/10 min	TEST & RECORD	ASTM D-1238	158.7 @ 190C 10KG
PELLET COUNT	pellets/g	50.0 + / - 10.0	MDSI	45
PELLET SIZE		#4= <1.0%		#4 = 0.00
DISTRIBUTION	%	#6+#8= 98.0% +	ASTM-1921	#6 & #8 = 99.90
		#12 = <1.0%		#12 = 0.10
MOISTURE	%	TEST & RECORD	MDSI	0.05
BULK DENSITY	lb/cft	TEST & RECORD	ASTM D-1895	43.95

Environmental Stress Cracking

Test to pass ASTM D1248. The standard calls for 80% retention after 48 hours. Both Dow 1310 and Exxon 9586 with 5% PR 2003 passed with 100% after 48 hours.

Sunlight Resistance

Samples passed 720 hours of conditioning with 80% retention.

1310 with 5% Black			9856 with 5% Black		
unaged	Psi	Elong. (%)	unaged	Psi	Elong.(%)
average	3450	718	average	3314	864
aged	Psi	Elong.(%)	aged	Psi	Elong.(%)
average	2765	799	average	3955	743

Tracking Resistance

Testing done in accordance with ASTM D2303 Passed.

Heat Deformation

Heat Deformation Testing was done in accordance with ICEA T-27-581

	Deformation	Maximum	Pass/fail
1310 with 5% Black	1.81%	30%	Pass
9586 with 5% Black	2%	30%	Pass

Processing Recommendations

PR-2003 BLACK must be fed into the extruder at a 5% addition rate and 95% of HDPE base resin. This blend can be extruded using a conventional extruder and screw. Suggested extrusion conditions are listed below. These conditions are intended as a general guideline only and are not optimum values because manufacturing conditions, such as extruder type and size, affect the processing of thermoplastic compounds.

<u>Extruder Zone</u>	<u>Temperature Range</u>
Z1 (Feed Throat)	350°F
Z2	400°F
Z3	450°F
Z4	475°F
Die	475°F
Melt Temperature	475°F
Wire Preheat	230°F

Liability

Information contained in this publication is accurate to the reasonable knowledge of the publisher. M. Holland does not accept any liability whatsoever arising out of the use of the information in this document or the use, application, adaptation or processing of the products described herein.

All information is given in good faith, without warranty, representation, inducement or license of any kind. No guarantee is given that M. Holland products will be suitable in purchasers' constructions or processes for any particular end use. No one is authorized to make representations or give warranties or assume any other liabilities on behalf of M. Holland except if in writing and signed by a duly authorized M. Holland employee.

The purpose of the information contained herein is to assist our present and potential customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products and to consult the related Material Safety Data Sheet before use in order to satisfy itself as to the contents of the products and the suitability of the products for the customer's particular purpose. Although the information contained herein is to our knowledge accurate and reliable as of the date hereof, nothing herein shall constitute any warranty (express or implied, of merchantability, fitness or otherwise) and no statement herein shall be construed as an endorsement of any product or process. M. Holland shall not be liable for special, incidental, or consequential damages arising out of the use of the products based upon a breach of warranty, breach of contract, negligence, strict tort liability or any other legal theory.