



TPE 5595 LSZH

Low Smoke Zero Halogen Flame Retardant Thermoplastic Elastomer (TPE)

Description

TPE 5595 LSZH is a natural, olefin-based thermoplastic elastomer (TPE) intended for wire and cable insulation and jacketing applications where high temperature performance and excellent flame resistance are required.

TPE 5595 LSZH contains a novel non-halogen intumescent flame retardant additive package designed to reduce normal PE flame spread characteristics and achieve a VW-1 flame resistant rating on 14 AWG wires and larger. It also offers good extrusion processing characteristics on either conventional polyethylene or PVC extrusion lines. In addition, **TPE 5595 LSZH** contains a UV stabilization additive package that provides effective long-term UV weather resistance.

TPE 5595 LSZH is readily pigmented to a variety of colors using standard wire and cable color concentrates designed for thermoplastic or crosslinked polyolefins.

Application

TPE 5595 LSZH is intended for 125°C UL rated appliance wire and other flame retardant insulation or jacketing constructions. Specifically, this product is rated a V-0 by UL Standard 94 at a minimum thickness of 0.062 inches. **TPE 5595 LSZH** is capable of achieving a VW-1 flame resistance on 14 AWG or larger conductors as per UL Standard 1581.

Specifications

Cables manufactured using **TPE 5595 LSZH** in accordance with standard industry practices should meet the following industry cable specifications:

- Underwriters Laboratories Standard 62 Class 1.14 and 1.18 for Jacketing
- Underwriters Laboratories Standard 62 Class 2.20 and 2.28 for Insulation
- Underwriters Laboratories Standard 62 Class 36 Insulation and Jacketing
- Underwriters Laboratories Standard 94 V-0
- Underwriters Laboratories Standard 758 Style 1722 Appliance Wire

General Processing Guidelines

Extrusion start-up and shut-down procedures are similar to those of polyethylene. Since these materials are noncorrosive or abrasive, no special recommendations are made for barrel and screw materials of construction. A suggested melt temperature of 390°F (199°C) should provide a good quality product. TPE exposure of these materials to elevated temperatures >450°F (230°C) for prolonged periods of time has been shown to decrease long-term stability. Preheating the conductor to 125-150°C is recommended during insulation extrusion to minimize orientation and internal stress that could result in poorer physical properties.

Physical Properties	Typical Value ⁽²⁾⁽⁴⁾	Unit	Test Method ⁽¹⁾
Density	1.05	g / cm ³	ASTM D 792
Tensile Strength	1,960 (13.7)	psi (Mpa)	ASTM D 412
Ultimate Elongation	630	%	ASTM D 412
Chord Modulus (0.5% to 1.0%)	35,387 (247)	psi (Mpa)	ASTM D 790
Heat Aging, 7 days at 158°C			UL 1581
Tensile Strength Retention	103	%	ASTM D 412
Ultimate Elongation Retention	86	%	ASTM D 412
Hardness, Shore A (15s delay)	93	-	ASTM D 2240
Brittleness Temperature	-35	°C	ASTM D 746
Limiting Oxygen Index	38	%	ASTM D 2863
Flammability	V-0	-	UL 94
Low Temperature Brittle Point	-35	°C	ASTM D 746
Electrical Properties	Typical Value ⁽²⁾⁽³⁾	Unit	Test Method ⁽¹⁾
Dielectric Constant (60 Hz)	2.41	-	ASTM D 150
Dissipation Factor (60 Hz)	0.003	-	ASTM D 150
Dielectric Strength	660	V / mil	ASTM D 149
Volume Resistivity	1.6 x 10 ¹⁶	Ω cm	ASTM D 257

Suggested Extrusion Equipment**Suggested Extrusion Conditions**

Extruder L/D:	20:1 (minimum)	Throat:	Water-cooled
Extruder L/D:	24:1 (preferred)	Zone 1:	370°F
Screw:	Barrier or Single Flight	Zone 2:	(188°C)
Compression Ratio:	2.7 to 3.5:1	Zone 3:	385°F
Die:	Smooth transition,	Zone 4:	(196°C)
	With >= 1/8 in. land	Head / Die:	390°F
	Die & Tip include angle: 22-35°		(199°C)
			395°F
			(202°C)

- (1) Tested in accordance with the latest issue of the designated Test Methods.
(2) Data represents typical values and should not be used for specification work.
(3) All electrical properties tested on a 0.075 inch thick molded plaque.
(4) All physical properties tested on a 0.030 inch thick extruded tape.

Liability

Information contained in this publication is accurate to the reasonable knowledge of the publisher. M. Holland does not accept any liability whatsoever arising out of the use of the information in this document or the use, application, adaptation or processing of the products described herein.

All information is given in good faith, without warranty, representation, inducement or license of any kind. No guarantee is given that M. Holland products will be suitable in purchasers' constructions or processes for any particular end use. No one is authorized to make representations or give warranties or assume any other liabilities on behalf of M. Holland except if in writing and signed by a duly authorized M. Holland employee. The purpose of the information contained herein is to assist our present and potential customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products and to consult the related Material Safety Data Sheet before use in order to satisfy itself as to the contents of the products and the suitability of the products for the customer's particular purpose. Although the information contained herein is to our knowledge accurate and reliable as of the date hereof, nothing herein shall constitute any warranty (TPEress or implied, of merchantability, fitness or otherwise) and no statement herein shall be construed as an endorsement of any product or process. M. Holland shall not be liable for special, incidental, or consequential damages arising out of the use of the products based upon a breach of warranty, breach of contract, negligence, strict tort liability or any other legal theory.